

EPONAC 7161 75 X LBC

PRODUCT DATA SHEET

REC/716175XLBC/061401/1

Description

Bisphenol A based solid resin, with low epoxy equivalent weight, in xylene solution. Special grade with low Bisphenol A free content.

Applications

Eponac 7161 75 X LBC is suitable for general purpose air drying and stoving paints. It is mainly used for anticorrosion paints.

Sales specification

Property	Value	Unit	Method
Epoxy equivalent weight (1)	440 - 470	g/eq.	ISO 3001
Solid content	74 - 76	%	SIR 10553
Colour	2 max.	Gardner Sc.	ASTM D 1544

(1) determined on the solution with reference to solid material

Typical Properties

Property	Value	Unit	Method
Bisphenol A free content	< 100	ppm	SIR 10539
Density at 25°C	1.09	g/cm ³	ASTM D 1475
Dynamic Viscosity at 25°C	9000	mPa.s	ASTM D 0445

Supply Form

- Drums - 200 Kg.
- Bulk

Storage stability

The product should be stored in the original containers, in dry ambient, protected against light and direct sun-rays at temperature ranging from 15 to 30°C. In these conditions it is stable for one year.

Safety

The product is harmful.

Further advices are given in the safety data sheet

Eponac®: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.