

EPOSIR[®] 7183 45 BC/BGA

PRODUCT DATA SHEET

REM/718340BCBGA/061101/1

Description

Bisphenol A based solid resin, with high epoxy equivalent weight, in Butylglycol/Butylglycol Acetate solvent solution (solvent ratio 3:1).

Applications

Eposir 7183 45 BC/BGA is suitable for can coating stoving lacquers.

Sales specification (provisional)

Property	Value	Unit	Method
Epoxy equivalent weight (1)	1450 - 1750	g/eq.	ISO 3001
Solid content	44 - 46	%	SIR 10553
Colour	4 max.	Gardner Sc.	ASTM D 1544
Dynamic viscosity at 25°C	1600 - 2200	m.Pa.s.	ASTM D 0445

(1) determined on the solution with reference to solid material

Typical Properties

Property	Value	Unit	Method
Density at 25°C	1.025	g/cm ³	ASTM D 1475

Supply Form

- Drums - 200 Kg.
- Bulk

Storage stability

The product should be stored in the original containers, in dry ambient, protected against light and direct sun-rays at temperature ranging from 15 to 30°C. In these conditions it is stable for one year.

Safety

The product is harmful.

Further advice are given in the safety data sheet

Eposir[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.