

SIRESTER[®] FSG 0819

**PRODUCT DATA
SHEET**
RP/0819/052021

Description

Unsaturated orthophthalic polyester resin, diluted in styrene, with low reactivity and medium viscosity.

Applications

SIRESTER FSG 0819 is a special material suitable for the production of flexible systems, in particular for gelcoat, bonding pastes and coating formulations; it provides excellent compatibility with different resins, pigments and fillers and very high elongation at break; this material is not supposed to be used as sole binder for glass fibre reinforced plastics.

Sales specification

Property	Value	Unit	Method
Acid number	< 20	mg KOH/gr	SIR 10231
Viscosity at 25 °C	350 - 550	mPa s	SIR 10015

Typical Properties

Property	Value	Unit	Method
Appearance	Clear		SIR 10010
Styrene content	34	%	SIR 10257
Hazen colour	< 70	Sc. Co/Pt	SIR 10007
Gel time at 25 °C ⁽¹⁾	13	minute	SIR 10234
Stability at 65 °C	6	day	SIR 10242

(1) Formulation: 100 gr resin + 0,20 ml Co (Oct) 6% + 1,50 ml MEKP-50.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.

Mechanical properties of pure cured resin (*)

Property	Value	Unit	Method
Barcol hardness	2		EN 59
Flexural strength	10	MPa	ISO 178
E-Module, flexion	220	MPa	ISO 178
Tensile strength	15	MPa	EN ISO 527
E-Module, tension	400	MPa	EN ISO 527
Elongation at break	50	%	EN ISO 527
HDT	< 20	°C	EN ISO 75 A

(*) Typical properties, not suitable for specification; postcuring cycle: 24 hours 25 °C + 2 hours 100 °C

Supply Form

Product is available in a 225 kg lined drum, 1000 kg container or in bulk.

Storage guidelines

The product is stable for 6 months if stored in the original unopened packaging, below 30 °C and away from direct sunlight and heat sources. Keep away from iron and copper salts, organic and inorganic peroxides.

Safety

The product is flammable and harmful. Further information is provided in the relevant safety data sheet.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.