

SIRESTER[®] VE 755/T

PRODUCT DATA SHEET

RP/VE755T/112021

Description

Bisphenol-A vinylester resin, diluted in acrylic monomer, thixotropic with medium viscosity and slow reactivity.

Applications

SIRESTER VE 755/T is a styrene-free material suitable for warm cure pipeline rehabilitation (relining applications), in particular for civil purposes: it provides efficient wetting capability, excellent chemical resistance and good mechanical strengths.

Sales specification

Property	Value	Unit	Method
Acid number	≤ 15	mg KOH/ g	SIR 10231

Typical Properties

Property	Value	Unit	Method
Appearance	Hazy	-	SIR 10010
Monomer content	41	%	SIR 10257
Thixotropic index at 25 °C	≥ 2,5		SIR 10215
- 2 rpm	≥ 3000	mPa.s	SIR 10215
- 20 rpm	≤ 1200	mPa.s	SIR 10215
Gel time at 60 °C ⁽¹⁾	17	minutes	SIR 10267
Time to peak	24	minutes	SIR 10267
Exothermic peak	180	°C	SIR 10267
Stability at 65°C	6	days	SIR 10242

(1) Formulation: 100 gr resin + 1,00 ml Co (oct.) 1% + 0,80% Perkadox 16 + 1,00% Trigonox C.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.

Mechanical properties of pure cured resin (*)

Property	Value	Unit	Method
Barcol hardness	50		EN 59
Flexural strength	100	MPa	ISO 178
E-Module, flexion	3900	MPa	ISO 178
Tensile strength	70	MPa	EN ISO 527
E-Module, tension	3700	MPa	EN ISO 527
Elongation at break	2,5	%	EN ISO 527
HDT	120	°C	EN ISO 75 A

(*) typical properties, not suitable for specifications; postcuring cycle: 24 hours 25 °C + 3 hours 100 °C

Mechanical properties of the reinforced resin (glass/resin 30/70) (*)

Property	Value	Unit	Method
Flexural strength	210	MPa	ISO 14125
E-Module, flexion	9000	MPa	ISO 14125
Tensile strength	110	MPa	EN ISO 527
E-Module, tension	9100	MPa	EN ISO 527

(*) typical properties, not suitable for specifications; postcuring cycle: 24 hours 25 °C + 3 hours 100 °C

Supply Form

Product is available in a 200 kg lined drum, 1000 kg container or in bulk.

Storage stability

The product is stable for 6 months if stored in the original unopened packaging), below 30 °C and away from direct sunlight and heat sources. Keep away from iron and copper salts, organic and inorganic peroxides; avoid carefully exposition to sunlight. Thixotropic properties are guaranteed for 3 months: a long period of storage can cause slight segregation of the solid part of the product. Stir the resin before use

Safety

The product is harmful. Further information is provided in the relevant safety data sheet.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.